

Utzon Nylon Rope

Weight & strength of 3-strand twisted ropes



The ropes are stabilized and heatset to avoid cold water shrinkage and twisting torque. Durable impregnation improves water repelling and abrasion resistance.

Diameter (mm)	Coil weight (kg)	Coil length (m)	Weight pr. meter (g)	Runnage (m/kg)	Average breaking strength	
					(ton)	(kN)
7	9,0	300	30	33,4	1,1	11,2
8	9,0	230	39	25,6	1,4	14,6
9	9,0	175	51	19,5	1,9	19,1
10	9,0	140	64	15,6	2,4	24,0
11	8,8	115	77	13,0	2,6	26,5
12	12,7	140	91	11,0	3,1	31,3
13	18,1	170	106	9,4	3,6	36,7
14	21,3	180	118	8,5	4,0	40,7
15	21,5	160	134	7,4	4,5	46,4
16	21,8	130	168	6,0	5,7	58,0
18	22,9	110	208	4,8	7,0	71,8